

Tray Orange

(B-TY10G)

Check: Well shaken resin, Clean optical pathways, Good resin tank condition.

Recommendation:

Prevention of cross-contamination with other non-bio resins ensures optimal biocompatibility for printed models. Dedicate accessories for Tray Orange: resin tank, build platform and wash.

Printer Settings:

Brand	Model	Settings
Formlabs	Form 4B	
Open system MSLA ● Elegoo ● Phrozen ● Anycubic	● Mars 5 Ultra, Saturn 4 ...etc. ● Mighty 12K, Sonic Mini 8K ...etc. ● M3 Premium ...etc.	To get the latest printing settings, simply visit the ApplyLabWork Support page and download the files for your printer model.
Asiga	Pro 4K UV385, Max UV385	
HeyGears	Reflex	PAU20 (100 µm)
SprintRay <small>(Not endorsed by SprintRay)</small>	Pro 2	Study model white 2 (100 µm)
	Pro 95 S	IDB 2 (100 µm)

Note: Each printer is unique, and light intensity can vary even among identical models. Minor adjustments may be necessary, especially true for open-system MSLA printers.

Cleaning: [fill fresh 95% IPA in two baths]

A-bath: Submerge and agitate printed models in IPA. Use toothbrush to gently remove uncured resin quickly on the model surfaces. Transfer cleaned model to B-bath.

B-bath: Submerge cleaned models from A-bath for **3 minutes**.

Total IPA clean time should not exceed 5 minutes.

Drying:

Blow dry the models with compressed air, let models **sit dry 25 minutes minimum** in a shaded airy place. Printed parts must be free of IPA before UV post-curing. Extended wash time and residual IPA (if not dried completely) causes deformation and lower mechanical properties.

UV Post-Curing Setting (Required):

Brand	Post-Curing Chamber Model	Settings
Elegoo	Mercury Cure	60 min
Formlabs	FormCure	60°C 30min
NK Optik	Otoflash	2000 flashes
HeyGears	UltraCraft Cure	PAWR10
SprintRay	Nano Cure	Try in 2
SprintRay	ProCure 2	Try in 2

Allow the models to cool naturally to room temperature after curing. (Avoid external forces, no stacking of models during cooling.)

Storage:

Filter out all debris in used-resin before storage. Keep resin in the original bottle, storage temp (15-26°C / 59-79°F) in a dry and dark area.

Note: Pigment settlement is normal. Gently mix remaining resin in resin tank with soft “resin wiper” for color evenness.